

GEN 2594 Welding Wire and Rod

GEN 2594 is a super-duplex stainless steel used for welding alloys with similar chemical composition such as S31260, S32750, S32760 and S32550. It can also be used for welding of carbon and low alloy steel to duplex stainless steel. The weld metal offers good resistance against stress corrosion cracking and pitting corrosion.

CONFORMANCES

AWS A5.9/A5.9M	:	ER2594
ASME SFA-A5.9	:	ER2594
ISO 14343B	:	SS2594

AWS CHEMICAL COMPOSITION (TYPICAL)

%C	%Cr	%Ni	%Mo	%Mn	%Cu
0.03 max 0.01	24.0 – 27.0 25	8.0 – 10.5 9.2	2.5 – 4.5 3.9	2.5 max 0.6	1.5 max 0.09
%Si	%P	%S	%W	%N	
1.0 max 0.4	0.03 max 0.02	0.02 max 0.01	1.0 max 0.02	0.08 – 0.20 0.25	

TYPICAL WELD METAL MECHANICAL PROPERTIES

Yield Strength	:	91,000 psi
Tensile Strength	:	121,000 psi
Elongation	:	20 %

TYPICAL WELDING PARAMETERS*

Process	Diameter		Voltage	Amperage	Gas/Flux
TIG (GTAW)	1/16"	1.6 mm	10 – 12	80 – 150	100% Ar
	3/32"	2.4 mm	15 – 18	150 – 250	100% Ar
	1/8"	3.2 mm	16 – 20	200 – 375	100% Ar
MIG (GMAW)	.035"	0.9 mm	29 – 34	150 – 180	98% Ar – 2% O ₂
	.045"	1.1 mm	29 – 34	180 – 220	98% Ar – 2% O ₂
Sub Arc (SAW)	.093"	2.4 mm	28 – 32	300 – 400	
	.125"	3.2 mm	29 – 33	400 – 500	

*All parameters are suggested as basic guidelines only and will vary depending on joint design, number of passes and other factors.

<p>IMPORTANT: SPECIAL VENTILATION AND/OR EXHAUST REQUIRED</p> <p>BEFORE USE, READ AND UNDERSTAND THE SAFETY DATA SHEET (SDS) FOR THIS PRODUCT AND SPECIFIC INFORMATION PRINTED ON THE PRODUCT CONTAINER.</p>

The contents of this document are presented for informational purposes only and while every effort has been made to ensure their accuracy, they are not to be construed as guarantees, express or implied, regarding the products or services described herein or their use or applicability. The user must fully evaluate every process and application in all aspects.