

GEN 308LSi Welding Wire and Rod

GEN 308LSi has the same chemical composition as GEN 308, except the higher silicon content. It is suitable for welding stainless steel type 304 and 308. Welding process can be done at a higher speed than GEN 308 and GEN 308L due to improved wettability of weld metal. The higher silicon content also provides better arc stability along with smoother bead appearance.

CONFORMANCES

AWS A5.9/A5.9M	:	ER308LSi
ASME SFA-A5.9	:	ER308LSi
UNS	:	S30888

AWS CHEMICAL COMPOSITION (TYPICAL)

%C	%Cr	%Ni	%Mo	%Mn
0.03 max. 0.018	19.5 – 22.0 19.81	9.0 – 11.0 9.65	0.75 max. 0.08	1.0 – 2.5 1.89
%Si	%P	%S	%Cu	
0.65 – 1.00 0.85	0.03 max. 0.02	0.03 max. 0.011	0.75 max. 0.15	

TYPICAL WELD METAL MECHANICAL PROPERTIES

Tensile Strength	:	87,000 psi	600 MPa
Yield Strength	:	59,000 psi	407 MPa
Elongation	:	40 %	

TYPICAL WELDING PARAMETERS

Process	Diameter		Voltage	Amperage	Gas/Flux
TIG (GTAW)	1/16"	1.6 mm	14 – 18	80 – 150	100% Ar
	3/32"	2.4 mm	15 – 20	150 – 250	100% Ar
	1/8"	3.2 mm	16 – 20	200 – 375	100% Ar
MIG (GMAW)	.035"	0.9 mm	23 – 29	170 – 290	98%Ar – 2%O ₂
	.045"	1.1 mm	24 – 30	200 – 360	98%Ar – 2%O ₂
Sub Arc (SAW)	.093"	2.4 mm	28 – 32	250 – 450	
	.125"	3.2 mm	29 – 34	300 – 500	

*All parameters are suggested as basic guidelines only and will vary depending on joint design, number of passes and other factors.

<p>IMPORTANT: SPECIAL VENTILATION AND/OR EXHAUST REQUIRED</p> <p>BEFORE USE, READ AND UNDERSTAND THE SAFETY DATA SHEET (SDS) FOR THIS PRODUCT AND SPECIFIC INFORMATION PRINTED ON THE PRODUCT CONTAINER.</p>

The contents of this document are presented for informational purposes only and while every effort has been made to ensure their accuracy, they are not to be construed as guarantees, express or implied, regarding the products or services described herein or their use or applicability. The user must fully evaluate every process and application in all aspects.